

Introduction

The layout of the surface mount board plays a critical role in product design and must be done properly to achieve the intended performance of an integrated circuit. An accurate PCB pad and solder stencil design provides a proper connection interface between the IC package and the board. With the correct pad geometry, the package will self-align when subjected to a solder reflow process and will also allow for just enough excess surface area for adequate solder filleting. The solder mask should be applied over bare copper (SMOBC) to avoid solder reflow under the solder mask.

These considerations apply in general for most of M/A-COM Tech's surface mount packaged IC's. This application note provides specific guidelines for mounting quad flat no-leads packages (QFN per JEDEC MO-220), and dual flat no-leads packages (DFN per JEDEC MO-229).

PCB Pad Design

1

Commitment to produce in volume is not due


The first consideration in mounting the QFN / DFN to a board is the layout of metalized pads. The US-based trade association, IPC, has developed land pad design standards contained in the document IPC-SM-782 entitled *Surface Mount Design and Land Pattern Standards*.

Figures 1-1 through 1-3 shows the PCB geometry developed for M/A-COM's QFN / DFN packages based on the general guidelines contained within IPC-SM-782. The center area or the thermal pad, acts as an RF ground pad and thermal path to conduct heat away from the package. Normally, the size of the thermal pad should match the size of the exposed pad on the bottom of the package. However, a smaller thermal pad is sometimes recommended to prevent solder bridging to the lead pads. Table 1 shows some suggested PCB pad dimensions for QFN / DFN packages used by M/A-COM Tech. The solderable length of the lead pad is controlled by the solder mask opening (Lm) as indicated in Table 2, in combination with pad length (L) as indicated in Table 1.

Via Design

To improve the thermal/RF performance of the package, we recommend providing thermal vias on the PCB. These vias provide a heat transfer and RF ground path from the top surface of the PCB to the inner layers and the bottom surface. We recommend a via diameter of 0.3 mm in a 1.0 mm pitch array for standard square packages. This is shown in Figure 1-1, in which the vias are 1.0 mm away from their diagonal neighbors. Other non-standard designs may require a slightly different via diameter and pitch as shown in Figures 1-2, 1-3, and 2-4.

Figure 1-1 PCB Land Design



ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. **PRELIMINARY:** Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples **and/or restronger may be available**. North America Tel: 800.366.2266
 Europe Tel: +353.21.244.6400
 India Tel: +91.80.43537383
 Visit www.macomtech.com for additional data sheets and product information.

ined herein without notice.

MA-COM Technology Solutions mc and its affiliates reserve the right to make

s) or information c

nges

to the proc

Rev. V10

Application Note S2083



Rev. V10

Surface Mount Instructions for QFN / DFN Packages







Figure 1-2 PCB Land Designs







• North America Tel: 800.366.2266 • Europe Tel: +353.21.244.6400 • India Tel: +91.80.43537383 • China Tel: +86.21.2407.1588 Visit www.macomtech.com for additional data sheets and product information.

changes to the proc

Application Note S2083



Rev. V10

Surface Mount Instructions for QFN / DFN Packages







Figure 1-3 PCB Land Designs - cont.







ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples mayor restruer may be available. Commitment to produce in volume is not guardited A

North America Tel: 800.366.2266
 Europe Tel: +353.21.244.6400
 India Tel: +91.80.43537383
 Visit www.macomtech.com for additional data sheets and product information.

M/A-COM Technology Solutions are rand is affiliates reserve the right to make Changes (It) the products) by information contained herein without notice.

Application Note S2083

Surface Mount Instructions for QFN / DFN Packages



Rev. V10

Package Description				PCB Land Pattern Dimensions (mm)			Max #	
Package Type	Size (mm)	No. of Leads	Lead Pitch (mm)	Тр	x	L	of Vias	
X1-DFN	1 x 1	6	0.35	Fig. 1-2	0.18	0.20	1	
PDFN	1.2 x 1.5	6	0.50	Fig. 1-2	0.25	0.40	1	
PDFN	1.5 x 1.2	6	0.40	Fig. 1-3	0.23	0.315	2	
PDFN	2 x 2	8	0.50	Fig. 1-2	0.28	0.40	3	
STQFN	2 x 2	12	0.40	0.82	0.23	0.34	4	
STQFN	2 x 2.5	14	0.40	Fig.1-3	0.23	0.34	6	
PQFN	3 x 3	12	0.50	1.2	0.28	0.65	2	
PQFN	3 x 3 (1.45 mm Exp. Pad)	16	0.50	1.5	0.28	0.50	2	
PQFN	3 x 3 (1.7 mm Exp. Pad)	16	0.50	1.6	0.28	0.45	2	
PQFN	4 x 4	16	0.65	2.2	0.37	0.65	5	
PQFN	4 x 4	20	0.50	2.2	0.28	0.65	5	
PQFN	4 x 4	24	0.50	2.55	0.28	0.50	5	
PQFN	4 x 6 (V1)	32	0.50	Fig. 1-3	0.28	0.50	5	
PQFN	5 x 5 (std)	20	0.65	3.2	0.37	0.65	9	
PQFN	5 x 5 (Power Amp.)	20	0.65	3.2	0.37	0.65	Fig.1-3	
PQFN	5 x 5	28	0.50	3.2	0.28	0.65	9	
PQFN	6 x 6	28	0.65	4.5	0.40	0.50	18	

Table 1. Recommended PCB Land Pattern Dimensions

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples mm/or restored mit be available. Commitment to produce in volume is not guaranteed.

4

North America Tel: 800.366.2266
 Europe Tel: +353.21.244.6400
 India Tel: +91.80.43537383
 Visit www.macomtech.com for additional data sheets and product information.

e. M/A-COM Technology Solutions and its affiliates reserve the right to make Changes to the products) by information contained herein without notice.



Rev. V10

Solder Mask Considerations


The solder mask, a permanent part of most PCB's applied after etching the metal pads, helps protect the spaces between the metal pads from solder paste and unintended adhesion of solder. All metalized pad areas on a printed circuit board can be classified as either solder mask defined (SMD) or non-solder mask defined (NSMD), depending on the size of the opening in the solder mask relative to the size of the metal pad.

An SMD metal pad has its periphery partly covered by the solder mask. An NSMD metal pad sits within a larger opening in the solder mask.

The copper etching process used to define metal pads provides tighter control than the solder mask process, so M/A-COM recommends using NSMD pads whenever possible. The recommended solder mask opening for all lead pads should be 140 microns larger than the pad size, which results in 70 microns clearance between the copper pad and solder mask. For example, the 4 x 4 mm 20lead package has an indicated width of the PCB lead pad (X) of 0.28 mm (Table 1) and the width of the solder mask opening (Wm) would be 0.42 mm (Table 2). In the other direction, the length of the solder mask opening (Lm) should be 180 microns extended outward from the edge of the package and 70 microns inward from the PCB pads, which results in a total length of 900 microns (see Table 2).

To avoid any solder bridging between the thermal pad and lead pads, we recommend making the thermal pad an SMD pad so that the solder mask defines the thermal land. The mask opening (Tm) should be 100 microns smaller than the recommended thermal land size, which would be 2.1 mm for the 4 mm PQFN package. See Table 2 for additional recommended thermal land solder mask opening dimensions.

To prevent solder wicking inside the via during reflow, we recommend solder mask pads over all The solder mask diameter thermal via areas. should be 100 microns larger than the via diameter. Based on our experience with suppliers, we have found fewer voids under the die paddle using solder mask printing on the top surface of the PCB, as compared with solder mask printing on the bottom. Filled vias also work well as an alternative to solder mask to further enhance thermal conduction for high power amplifier products (see These printed boards should also figure 1-3). include 1 oz. copper plating in vias which are subsequently filled with a conductive via fill material and then over-plated. It is recommended that there be 2 oz. final copper thickness on the thermal pad for optimal heat transfer.



nges

Figure 2-1 Solder Mask Designs

5

typical. Mechanical outline has been fixed. Engineering samples

Commitment to produce in volume is not du


• China Tel: +86.21.2407.1588 Visit www.macomtech.com for additional data sheets and product information. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are ailable M/A-COM Techrology Solutions no and its affiliates reserve the right to make

ined herein without notice.

n ormation c



Rev. V10




6

- ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions • North America Tel: 800.366.2266 • Europe Tel: +353.21.244.6400 is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology • India Tel: +91.80.43537383 Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples Commitment to produce in volume is not duardited. may be ailable.
 - China Tel: +86.21.2407.1588 Visit www.macomtech.com for additional data sheets and product information.

M/A-COM Technology Solutions mc, and its affiliates reserve the right to make Changes to the product(s) of information contained herein without notice.



Rev. V10






7

is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. **PRELIMINARY:** Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples Commitment to produce in volume is not duardited. nav be ailable.

M/A-COM Technology Solutions more and its affiliates reserve the right to make Changes to the proceed is on in ormation contained herein without notice.



Rev. V10





Stencil Design

A stencil is used for applying solder paste to the Although the PCB design suggested in PCB. Figures 1 through 2 will help eliminate some surface mounting difficulties, special considerations apply in stencil design and solder paste printing for both lead pad and thermal pads.

Surface mount processes vary from company to company, so we recommend careful development of your process for QFN / DFN packages. The following provides some guidelines for stencil design.

We recommend a stencil thickness of 0.100 to 0.125 mm for fine pitch packages (0.5 mm or smaller). This thickness can be increased to 0.15 mm for coarser pitch parts. A laser-cut, stainless steel stencil with electro-polished trapezoidal walls is recommended.

The stencil opening for all lead pad areas should be the same as the pad size on the PCB (Tables 1 & 2). As mentioned before, the function of the thermal pad is to allow for heat removal from the package as well as providing an effective RF ground. Therefore, a good stencil design becomes important for getting an optimal older paste distribution between the lead pads and the thermal pad. To minimize voids and defects, use smaller multiple stencil openings for the thermal pad instead of one big opening. Figures 3-1 through 3-3 shows the recommended stencil designs. The target coverage for solder paste area is to maintain 50 to 80 percent of the overall thermal pad area. The selected web width is 0.2 mm running across the vias as shown in Figures 3-1 through 3-3.

ined herein without notice.

n ormation c

⁸

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results. and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples ailable M/A-COM Techrology Solutions no and its affiliates reserve the right to make Commitment to produce in volume is not du to the l nges

[•] North America Tel: 800.366.2266 • Europe Tel: +353.21.244.6400 • India Tel: +91.80.43537383 • China Tel: +86.21.2407.1588 Visit www.macomtech.com for additional data sheets and product information.

Application Note S2083



Surface Mount Instructions for QFN / DFN Packages

Rev. V10




Figure 3-1 Stencil Designs

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are MA-COM Technology Solutions morand its iffiliates reserve the right to make Changes to the product(s) on in ormation contained herein without notice. typical. Mechanical outline has been fixed. Engineering samples Commitment to produce in volume is not duardited. A nav be ailable.

• North America Tel: 800.366.2266 • Europe Tel: +353.21.244.6400 • India Tel: +91.80.43537383 • China Tel: +86.21.2407.1588 Visit www.macomtech.com for additional data sheets and product information.

9

Application Note S2083



Surface Mount Instructions for QFN / DFN Packages

Rev. V10





Figure 3-2 Stencil Designs - cont.





change s

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions • North America Tel: 800.366.2266 • Europe Tel: +353.21.244.6400 is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. • India Tel: +91.80.43537383 • China Tel: +86.21.2407.1588 Visit www.macomtech.com for additional data sheets and product information. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are M/A-COM Technology Solutions mc, and its iffiliates reserve the right to make Changes to the products) on mormation contained herein without notice. typical. Mechanical outline has been fixed. Engineering samples Commitment to produce in volume is not duardited. nav be ailable.

Application Note S2083

Surface Mount Instructions for QFN / DFN Packages



Rev. V10

Package			Solder Mask Opening (mm)				Stencil Opening (mm)			
type	mm	leads	Wm	Lm	Tm	Am	х	Lst	Tst	Ast
X1-DFN	1 x 1	6	Fig. 2-2	Fig. 2-2	Fig. 2-2	1.30	0.18	0.35	Fig. 3-1	1.30
PDFN	1.2 x 1.5	6	0.39	0.65	Fig. 2-2	1.56	0.25	0.58	Fig. 3-1	1.56
PDFN	1.5 x 1.2	6	Fig. 2-2	0.565	Fig. 2-2	1.86	0.23	0.495	Fig. 3-1	1.86
PDFN	2 x 2	8	0.42	0.65	Fig. 2-3	2.36	0.28	0.58	Fig. 3-1	2.36
STQFN	2 x 2	12	Fig. 2-3	0.59	0.72	2.36	0.23	0.52	0.62	2.36
STQFN	2 x 2.5	14	Fig. 2-3	0.59	Fig. 2-3	Fig. 2-3	0.23	0.52	Fig. 3-1	Fig. 3-1
PQFN	3 x 3	12	0.42	0.90	1.1	3.36	0.28	0.83	1.0	3.36
PQFN	3 x 3 (1.45 mm Exp. Pad)	16	0.42	0.75	1.4	3.36	0.28	0.68	1.3	3.36
PQFN	3 x 3 (1.7 mm Exp. Pad)	16	0.42	0.70	1.5	3.36	0.28	0.63	1.4	3.36
PQFN	4 x 4	16	0.51	0.90	2.1	4.36	0.37	0.83	2.0	4.36
PQFN	4 x 4	20	0.42	0.90	2.1	4.36	0.28	0.83	2.0	4.36
PQFN	4 x 4	24	0.42	0.75	2.45	4.36	0.28	0.68	2.3	4.36
PQFN	4 x 6 (V1)	32	0.42	0.75	Fig. 3-3	Fig. 3-3	0.28	0.68	Fig. 3-3	Fig. 3-3
PQFN	5 x 5 (std)	20	0.51	0.90	3.1	5.36	0.37	0.83	3.0	5.36
PQFN	5 x 5 (Power Amp.)	20	0.51	0.90	3.1	5.36	0.37	0.83	3.0	5.36
PQFN	5 x 5	28	0.42	0.90	3.1	5.36	0.28	0.83	3.0	5.36
PQFN	6 x 6	28	0.54	0.75	4.4	6.36	0.40	0.68	4.3	6.36

Table 2. Recommended Solder Mask & Stencil Dimensions

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples mm/or restored mit be available. Commitment to produce in volume is not guaranteed.

11

North America Tel: 800.366.2266
 Europe Tel: +353.21.244.6400
 India Tel: +91.80.43537383
 Visit www.macomtech.com for additional data sheets and product information.

MA-COM Technology Solutions and its affiliates reserve the right to make changes fit the products) on information contained herein without notice.





Rev. V10

Reflow Profile

The most common solder reflow method is accomplished in a belt furnace using convection heat transfer. Tables 3 thru 5 along with Figure 4 show a typical convection reflow profile of temperature versus time. The profile reflects the three distinct heating stages, or zones (preheat, reflow, and cooling) recommended in automated reflow processes to ensure reliable, finished solder joints. The profile will vary among soldering systems and is intended as an example to use as a starting point. Other factors that can affect the profile include the density and types of components on the board, type of solder used and type of board or substrate material being used.

Thermocouples should be securely attached to the top surface of a representative component to insure the temperature exposure is met. Profile should be recorded by data acquisition for future reference.

General Soldering Precautions

The melting temperature of solder generally exceeds the recommended maximum operating temperature of the device. When the entire device is heated to a high temperature, failure to complete soldering within a short time could result in device failure. Therefore, always observe the following instructions to minimize the thermal stress to the devices.

- Always preheat the device (failure to do so can cause excessive thermal shock and stress that can result in damage to the device).
- Limit the temperature in the reflow stage to peak temperature indicated in Tables 3 thru 5.
- After completing the soldering process, allow the devices to cool naturally for at least 3 minutes. Gradual cooling should be used, as the use of forced cooling will increase the temperature gradient and may result in latent failure due to mechanical stress.
- Avoid any mechanical stress or shock to the solder joints and devices during cooling.

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples and/or rest-durate may be available. Commitment to produce in volume is not durinteed.

12

M/A-COM Technology Solutions and its affiliates reserve the right to make Changes to the product is) of in ormation contained herein without notice.



Rev. V10

Table 3. Reflow Conditions

Profile Feature	Sn-Pb Eutectic Assembly	Pb-Free Assembly	
Preheat/Soak Temperature Min (Ts _{min}) Temperature Max (Ts _{max}) Time (t _s) from (Ts _{min} to Ts _{max})	100°C 150°C 60 - 120 seconds	150°C 200°C 60 - 120 seconds	
Ramp-Up Rate (T⊾ to Tp)	3°C/second max.	3°C/second max.	
Liquidous temperature (T _L) Time (t _L) maintained above T _L	183°C 60 - 150 seconds	217°C 60 - 150 seconds	
Peak package body temperature (Tp)	For users T_P must not exceed the Classification temperature in Table 4 For suppliers T_P must not exceed the Classification temperature in Table 4	For users T_P must not exceed the Classification temperature in Table 5 For suppliers T_P must not exceed the Classification temperature in Table 5	
Time (tp)* within 5 °C of the specified Classification temperature (T _C), see reflow profile	20* seconds	30* seconds	
Ramp-Down Rate (Tp to T⊾)	6°C/second max.	6°C/second max.	
Time 25°C to Peak Temperature	6 minutes max.	8 minutes max.	

Note 1: All temperatures refer to the center of the package, measured on the package body surface that is facing up during assembly reflow (e.g., live-bug). If parts are reflowed in other than the normal live-bug assembly reflow orientation (i.e., dead-bug), T_P shall be within ± 2 °C of the live-bug T_P and still meet the To requirements, otherwise, the profile shall be adjusted to achieve the latter. To accurately measure actual peak package body temperatures refer to JEP140 for recommended thermocouple use.

Note 2: Reflow profiles in this document are for classification/preconditioning and are not meant to specify board assembly profiles. Actual board assembly profiles should be developed based on specific process needs and board designs and should not exceed the parameters in Table 3

For example, if Tc is 260 °C and time tp is 30 seconds, this means the following for the supplier and the user.

For a supplier. The peak temperature must be at least 260 °C. The time above 255 °C must be at least 30 seconds.

For a user: The peak temperature must not exceed 260 °C. The time above 255 °C must not exceed 30 seconds.

Note 3: All components in the test load shall meet the classification profile requirements.

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions

is considering for development. Performance is based on target specifications, simulated results,

PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology

and/or prototype measurements. Commitment to develop is not guaranteed.

typical. Mechanical outline has been fixed. Engineering samples

Commitment to produce in volume is not due

Note 4: SMD packages classified to a given moisture sensitivity level by using Procedures or Criteria defined within any previous version of J-STD-020, JESD22-A112 (rescinded), IPC-SM-786 (rescinded) do not need to be reclassified to the current revision unless a change in classification level or a higher peak classification temperature is desired.

may be

ailable.

Table 4. SnPb Eutectic Process - Classification Temperature (T_c)

Package Thickness	Volume mm ³ <350	Volume mm³ ≥350		
<2.5 mm	235°C	220°C		
≥2.5 mm	220°C	220°C		

Visit www.macomtech.com for additional data sheets and product information. Solutions has under development. Performance is based on engineering tests. Specifications are

M/A-COM Technology Solutions mc, and its affiliates reserve the right to make Changes to the product(s) of information contained herein without notice.

[•] North America Tel: 800.366.2266 • Europe Tel: +353.21.244.6400 • India Tel: +91.80.43537383 • China Tel: +86.21.2407.1588



Rev. V10

Table 5. Pb-Free Process - Classification Temperature (T_c)

Package Thickness	Volume mm ³ <350	Volume mm ³ 350-2000	Volume mm ³ >2000	
<1.6 mm	260°C	260°C	260°C	
1.6 mm-2.5 mm	260°C	250°C	245°C	
>2.5 mm	250°C	245°C	245°C	


Note 1: At the discretion of the device manufacturer, but not the board assembler/user, the maximum peak package body temperature (T_p) can exceed the values specified in Tables 4 or 5. The use of a higher T_p does not change the classification temperature (T_c).

Note 2: Package volume excludes external terminals (e.g., balls, bumps, lands, leads) and/or nonintegral heat sinks.

Note 3: The maximum component temperature reached during reflow depends on package thickness and volume. The use of convection reflow processes reduces the thermal gradients between packages. However, thermal gradients due to differences in thermal mass of SMD packages may still exist. Note 4: Moisture sensitivity levels of components intended for use in a Pb-free assembly process shall be evaluated using the Pb-free classification temperatures and profiles defined in Tables 3 and 5, whether or not Pb-free.

Note 5: SMD packages classified to a given moisture sensitivity level by using Procedures or Criteria defined within any previous version of J-STD-020, JESD22-A112 (rescinded), IPC-SM-786 (rescinded) do not need to be reclassified to the current revision unless a change in classification level or a higher peak classification temperature is desired





14

ADVANCED: Data Sheets contain information regarding a product M/A-COM Technology Solutions is considering for development. Performance is based on target specifications, simulated results, and/or prototype measurements. Commitment to develop is not guaranteed. PRELIMINARY: Data Sheets contain information regarding a product M/A-COM Technology Solutions has under development. Performance is based on engineering tests. Specifications are typical. Mechanical outline has been fixed. Engineering samples malor restorements be available. Commitment to produce in volume is not durintified. North America Tel: 800.366.2266
 Europe Tel: +353.21.244.6400
 India Tel: +91.80.43537383
 Visit www.macomtech.com for additional data sheets and product information.

MA-COM Technol gy Solutions mc and its rifiliates reserve the right to make Changes to the product (s) of in ormation contained herein without notice.